

Product Code	VLT %	VLR %	UV Transmission %	Summer U-Factor W/m2K	Winter U-Factor W/m2K	Shading Coefficient	Solar Energy Transmission %	Solar Energy Reflectance %	Solar Energy Absorption %	TSER %	* IGDB ID#
Ornyx Steel 5	7.8	15.6	<1	5.10	5.67	0.34	6.8	17.3	75.9	71.0	1721
Ornyx Steel 10	14.0	24.0	<1	5.17	5.74	0.36	11.0	23.0	66.0	70.0	1712
Ornyx Steel 20	26.0	14.0	<1	5.35	5.91	0.49	25.0	17.0	58.0	58.0	1713
Ornyx Steel 30	33.0	23.0	<1	5.35	5.91	0.50	28.0	21.0	51.0	57.0	1710
Ornyx Steel 41	42.0	18.0	<1	5.43	5.99	0.58	36.0	17.0	47.0	50.0	1707
Ornyx Steel 50	53.2	12.5	<1	5.50	6.05	0.67	44.0	10.9	45.1	42.0	1725
Ornyx Steel 60	64.5	9.8	<1	5.60	6.14	0.78	57.1	8.5	34.4	32.0	1726
Dualis 30	31.0	13.0	<1	5.36	5.90	0.52	25.0	14.0	61.0	55.0	1759
Dualis 40	45.0	10.0	<1	5.48	6.01	0.63	37.0	10.0	53.0	46.0	1758
Dualis 50	50.0	14.0	<1	5.36	5.90	0.66	42.0	14.0	44.0	43.0	1757